

Application/产品应用:  
Used for Hydraulic Oil filter

Characteristics/特性:  
Phenol impregnated cellulose and synthetic fiber  
Corrugated version  
Curing condition: 10min @ 180°C

CB230216

Physical properties 物理指标	Units 单位			
Mass per unit area 单位定量		G/m <sup>2</sup>	SD 固化前 SDC 固化后	162 155
Thickness 厚度		mm	Total 总厚度 Caliper 纸张厚度	0.81 0.50
Air permeability 透气度	200 Pa	l/m <sup>2</sup> .sec		243
Burst Strength 耐破度		kpa	SD 固化前 SDC 固化后	247 331
Stiffness 挺度		mN.m	SD 固化前 SDC 固化后	11 13
Pore Size 孔径		μm	Max 最大孔径	51

The above figures are written based on actual physical properties of trial production.  
The grade name and some physical properties would be adjusted after mass production.