

CTRFS9251



For Mobile and Industrial Fuel Applications

Supporting the industries' challenging new emission laws – H&V diesel fuel filter media provides consistent particulate and water protection while it lowers energy usage and extends the life of system components.

H&V produces a complete line of particulate and water coalescing media products used in on-highway and off-road applications. Specific grades address special market needs for challenging fuel quality, biofuel compatibility and static mitigation.

		Target	Test Method
BASIS WEIGHT: (as is)	(g/m ²)	269	TAPPI 410
(克重)	(lb/3,000ft ²)	166	
CALIPER (1.5 PSI)	(mm)	0.99	TAPPI 411
(总厚度)	(in)	0.039	1.5 PSI
CALIPER - CORRUGATION: (1.5 PSI)	(mm)	0.15	TAPPI 411
(瓦楞深度)	(in)	0.006	1.5 PSI
PERMEABILITY: (0.5" Water @ 200 Pa)	(l/m ² /sec)	12	20mm WG
(空透)	(CFM)	1.5	0.5" H2O
PARTICLE CAPTURE EFFICIENCY (4微米颗粒去除效率)	(%)	98.5	ISO 19438 4 μm particles
DUST HOLDING CAPACITY (单纸容尘量)	(g/m ²)	240	ISO 19438 0.5L/Min Test dust: PTI(11779M)
MAX PORE DIAMETER (最大孔径, IPA冒泡法)	(μm)	16	ASTM F316
TENSILE STRENGTH - MD dry (MD抗张强度, 干)	(kN/m)	9.0	TAPPI 494
	(lbs/inch)	51	
TENSILE STRENGTH - CD dry (CD抗张强度, 干)	(kN/m)	4.1	TAPPI 494
	(lbs/inch)	23	
MULLEN BURST (dry) (耐破度, 干)	(kPa)	490	TAPPI 403
	(psi)	71	
STIFFNESS - MD (cured, dry) (MD挺度, 固化后, 干)	(mg)	8000	TAPPI 543